

MH-FLON-B

General Information

MH-FLON-B is a PTFE (Polytetrafluorethylene) filled with 40% bronze and 3% Molybdenumdisulfide (MoS₂). The bronze fillers improve the wear resistance and compressive strength of the material and make it more resistant to extrusion. MoS₂ improves the gliding properties. It has similar chemical resistance and can be used in the same temperature range like virgin PTFE. PTFE shall not be used for dynamic applications in water.

PHYSICAL PROPERTIES

Colour:	brown		
Hardness at 20°:	DIN 53505	Shore D	70 - 80
Density:	DIN 53479	g/cm ³	3.25
Tensile strength:	DIN 53504	N/mm ²	> 15
Elongation at break:	DIN 53504	%	> 150
Coefficient of friction (dyn.):	ASTM D1894	μ	0.2
Wear factor (K):	ASTM D3702	3min 10-8/kg r	-
Compr. strength at 1% deform.:	ASTM D695	N/mm ²	-
Therm. Exp. Coeff. (lin.) 25-100°:	ASTM D696	10-5/°C	-
Min. service temperature:		°C	- 200
Max. service temperature:		°C	+ 260

Remark

All test methods and values mentioned above are corresponding to ASTM or DIN standards and have been tested on standardized plates in the laboratory. All tests are made under laboratory conditions.

MH Hydraulics BV

P.O. Box 275, 3200 AG Spijkenisse (Rotterdam), The Netherlands

P +31 (0)181 652880 , F +31 (0)181 621661, E info@mh.nl

www.mh.nl

MH HYDRAULICS. DIFFER TO BE BETTER.