

# MH-PUR

## General Information

MH-PUR is a MDI based polyurethane system which has been specially modified and developed for sealing applications. MH-PUR has been optimized in regards to its mechanical properties and stability in mineral and synthetic oils, gasoline, acid and basic environment. It has high tensile strength, very high abrasion resistance, low hysteresis, very good flexibility at low temperatures (-30/-40 °C) and low compression-set.

### PHYSICAL PROPERTIES

Colour:	green		
Hardness at 20°:	DIN 53505	Shore A	94 +/-2
Density:	DIN 53479	g/cm <sup>3</sup>	1.17
100% Modulus:	DIN 53504	N/mm <sup>2</sup>	> 12
300% Modulus:	DIN 53504	N/mm <sup>2</sup>	> 30
Tensile strength:	DIN 53504	N/mm <sup>2</sup>	> 55
Elongation at break:	DIN 53504	%	> 440
Rebound resilience:	DIN 53512	%	> 51
Tear strength:	DIN 53515	N/mm <sup>2</sup>	> 115
Abrasion:	DIN 53516	mm <sup>3</sup>	< 15
Compression set:*	DIN 53517	%	< 20
Min. service temperature:		°C	-35
Max. service temperature:		°C	110

\* Compression set: 70°C, 23 hours, 25% deflexion.

## Remark

All test methods and values mentioned above are corresponding to ASTM or DIN standards and have been tested on standardized plates in the laboratory. All tests are made under laboratory conditions.

### MH Hydraulics BV

P.O. Box 275, 3200 AG Spijkenisse (Rotterdam), The Netherlands

P +31 (0)181 652880 , F +31 (0)181 621661, E info@mh.nl

[www.mh.nl](http://www.mh.nl)

**MH HYDRAULICS. DIFFER TO BE BETTER.**